

# FERRITIC AND MARTENSITIC STEELS, INCL. PRECIPITATION HARDENING STEELS

## Available Product Variants

Plates

## Product Description

Sheets and Plates for the production of etched Pressplates for the production of decorative laminates (furniture industry, flooring)

## Process Melting

ESR

## Applications

> Press Plates

## Technical data

Material designation		
	1.4542	SEL
	630	AISI

## Chemical composition (wt. %)

C	Cr	Mo	Ni	Cu	Nb
≤ 0,04	16	0.2	4.5	3.3	0.25

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG  
Mariazeller Straße 25  
8605 Kapfenberg, AT  
T. +43/50304/20-0  
E. info@bohler-edelstahl.at  
<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.