

ACEROS AUSTENÍTICOS

Application Segments

Engineering

Formatos disponibles

Productos largos

Descripción

BÖHLER P558 is a high nitrogen 11% manganese-17% chromium-3% molybdenum-nickel stainless steel for surgical implants. Metallurgical requirements include a delta ferrite-free, fine-grained austenitic microstructure with low inclusion content and resistance to intergranular corrosion.

BÖHLER P558 exhibits pitting and crevice corrosion resistance much better than the reference material of Specification F138 and exceeds the material values given in Specification F1314 and Specification F1586. The biocompatibility tests for this material were positive and met the requirements of the test standards used.

The chemical composition of this steel has a high carbon content, together with high nitrogen content. The high carbon content is considered critical in conventional metallurgy of chromium-nickel stainless steels. In nitrogen-rich stainless steels, the carbon replaces the nitrogen, making it a strong contribution to the stabilisation of the austenitic phase. The simultaneous alloying of nitrogen and carbon has a beneficial effect on corrosion resistance and extends the range of austenite stability towards lower solution heat treatment temperatures, leading to better toughness properties.

Método de obtención

Airmelted + PESR

Aplicaciones

➤ Industria médica ➤ Instrumental médico e implantes ➤ Luxury Watch Industry (SP)

Datos técnicos

Designación	Estándares	
1.3808	SEL	F2581
X20CrMnMoN17-11-3	EN	ASTM
S29225	UNS	

Composición Química

C	Si	Mn	P	S	Cr	Mo	Ni	Cu	Fe	N
0,15 a 0,25	0,2 a 0,6	9,50 a 12,50	máx. 0,020	máx. 0,010	16,50 a 18,00	2,70 a 3,70	máx. 0,05	máx. 0,25	REM	0,45 a 0,55

Related to ASTM F2581.

Estado de suministro

Solution Annealed + Quenched

Resistencia a la tracción (MPa)	mín. 827
Resistencia a la cesión (MPa)	mín. 482

Barras redondas

Diámetro*		
mm		
FORZADO		
5,00	-	13,50
12,50	-	65,00

* Diameter 5.00 - 13.50 mm available as Wire Rod.

Diameter 12.5 - 65 mm round bars.

More information regarding MOQ, lengths and tolerances upon request.

For additional specifications and other sizes please contact BÖHLER Edelstahl - Special Materials Engineering

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.