

ACEROS RÁPIDOS

Formatos disponibles

Productos largos*
Chapas

*) Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Descripción

BÖHLER S630 - "El económico"

Acero rápido al tungsteno-molibdenu con aluminio para lograr una alta tenacidad y buena maquinabilidad. De utilización universal para mechas y machos de roscar, escariadores, brochas, sierras para metales, fresas de todo tipo y herramientas de carpintería.

Método de obtención

Convencional

Propiedades

- > Dureza y Ductilidad : alto
- > Resistencia al desgaste : alto
- > Resistencia a la compresión : alto
- > Estabilidad de los bordes : muy alta
- > Afilabilidad : buena
- > Dureza en caliente (dureza roja) : alto

Aplicaciones

- > Conformado en frío / acuñado
- > Corte fino / Troquelado / Estampado
- > Compactación de polvo
- > Laminación
- > Cizallas / Cuchillas
- > Herramientas de corte especiales
- > Componentes estándar (moldes, placas, expulsores, punzones)
- > Brocas helicoidales y grifos
- > Componentes de desgaste

Datos técnicos

Designación	
1.3330	SEL
HS 4-4-2 Al	EN

Composición Química

C	Cr	Mo	V	W	Al
0,95	4,00	4,00	2,00	4,00	0,50

Características

	Resistencia a la compresión	Aptitud para el rectificado	Dureza en caliente	Tenacidad	Resistencia al desgaste	Retención del filo de la navaja
BÖHLER S630	★★★	★★★	★★★	★★	★★	★★★
BÖHLER S200	★★★	★★	★★★	★★	★★★	★★
BÖHLER S400	★★★	★★★	★★★	★★★	★★	★★
BÖHLER S401	★★	★★★	★★	★★★	★★	★★★
BÖHLER S404	★★	★★★	★★	★★★	★★	★★
BÖHLER S430	★★	★★★	★★	★★★	★★	★★
BÖHLER S500	★★★★	★★★	★★★★	★★	★★★	★★★
BÖHLER S600	★★★	★★★	★★★	★★	★★	★★★
BÖHLER S607	★★★	★★★	★★★	★★	★★★	★★★
BÖHLER S705	★★★	★★★	★★★★	★★	★★	★★★★
BÖHLER S730	★★★	★★★	★★★★	★★	★★	★★★★

Estado de suministro

recocido

Dureza (HB)	máx. 280
Resistencia a la tracción (MPa)	máx. 950

Tratamiento térmico

Recocido

Temperatura	770 a 840 °C	Controlled slow cooling in furnace (10 - 20°C / h / (50 - 68°F 7 h) to approx. 600°C (1110°F), air cooling.
-------------	--------------	---


Alivio de tensiones

Temperatura	600 a 650 °C	Slow cooling furnace. To relieve stresses set up by extensive machining or in tools of intricate shape. After through heating, hold in neutral atmosphere for 1 to 2 hours.
-------------	--------------	---

Temple y revenido

Temperatura	1.050 a 1.200 °C	Salt bath, vacuum Preheating: 1st stage ~ 500 °C, 2nd stage ~ 850 °C, 3rd stage ~ 1050 °C (for higher austenitising temperature) Austenitising: for cutting applications at higher austenitising temperatures (> 1130 °C), holding time after complete heating 80 seconds, maximum 150 seconds, to avoid material damage due to overtime. Austenitising: for cold work applications at lower austenitising temperatures (< 1100°C). Holding time after complete heating 15 to 30 min Quenching: oil, warm bath (500 - 550 °C), gas.
Temperatura	550 a 570 °C	Slow heating to tempering temperature immediately after austenitising. Dwell time in the furnace 1 hour per 20 mm material thickness (at least 1 hour) Slow cooling to room temperature after each tempering step 3 tempering cycles recommended Hardness see tempering chart


Continuous cooling CCT curves



Austenitising temperature: 1210°C (2210°F)
Holding time: 180 seconds

- A....Austenite
- B....Bainite
- K....Carbide
- P....Pearlite
- M....Martensite
- RA...Retained Austenite

Tempering Chart



Holding time 3 x 2 hours
Specimen size: square 25 mm

Propiedades físicas

Temperatura (°C)	20
Densidad (kg/dm ³)	7,88
Conductividad térmica (W/(m.K))	18,8
Calor específico (kJ/kg K)	0,432
Resistencia eléctrica específica (Ohm.mm ² /m)	0,56
Módulo de elasticidad (10 ³ N/mm ²)	217

Long Products: For additional specifications and technical requirements, please contact our regional voestalpine BÖHLER sales companies.

Sheet & Plates: Product Variant may differ in terms of melting process, technical data, delivery, and surface condition as well as available product dimensions. Please contact voestalpine BÖHLER Bleche GmbH & Co KG.

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.